

Solvent Base Opaque Sanding Sealers

Rudd Prod. #	Product	% Solids by Weight	Viscosity Zahn #2 - Secs.	Sag Resistance - Miis	Catalyst Amount Oz/Gal	Pot Life - Hours	Dry to Sand - Minutes	VOC grams/liter	Lbs. HAPs/Lbs. Solids	Shelf Life - Months
Opaque Conversion Varnish Sanding Sealers (Primers)										
310668	MiraVar™ 275 Opaque CV Sanding Sealer- White	55.7%	30-36	5	4	8	45	223*	0.015	12
		Max Tint: 8 fl. oz. of colorant per gallon of coating. Fills edges on MDF. Fast, easy sanding. Super-Low HAP.								
310704	MiraVar™ 550 Opaque CV Sanding Sealer - White	65.5%	70-80 KU	9	4	24	30	442	0.247	12
		Max Tint: 4 fl. oz. of colorant per gallon of coating. Fast, easy sanding. Excellent build. Fills edges on MDF. Ultra-Low HAP.								
310670	Scion™ ZF 550 Opaque Formaldehyde Free CV Sealer - White	52.3%	70 KU	7	4	24	25	526	0.016	12
		Max Tint: 4 fl. oz. of colorant per gallon of coating. Zero formaldehyde resin technology. Color stable. Super-Low HAP.								
Opaque Pre-Catalyzed Sanding Sealers (Primers)										
652054	ChromaCat™ 275 Opaque PreCat Sanding Sealer - White	38.9%	19-25	5	n/a	n/a	20	274	0.0034	6
		Max Tint: 8 fl. oz. of colorant per gallon of coating. Excellent hide. Easy sand. Fast dry. Ultra-Low HAPs.								
651947	ChromaCat™ 680 Opaque PreCat Lacquer Sanding Sealer - White	34.5%	62-68 KU	10	n/a	n/a	20	640	0.017	12
		Max Tint: 8 fl. oz. of colorant per gallon of coating. Excellent hide. Easy sand. Fast dry. Thin only amount for use in 24 hours. Ultra-Low HAPs.								
Opaque Lacquer Sanding Sealer (Primer)										
653025	Pro Hi-Build™ 680 Opaque Lacquer Sanding Sealer/Undercoater - White	42.0%	95-105 KU	12	n/a	n/a	20	680	0.259	12
		Do not use under opaque (pigmented) CV. Fast Dry. Easy sand. Excellent hide. Thin only amount for use in 24 hours. Low HAP.								
Opaque Universal Undercoater - Water Base										
280187	Universal Hi-Build™ Water Base Opaque Undercoater	58.5%	65-70 KU	7	n/a	n/a	30	76	0.000	12
		Compatible with most water base and solvent base topcoats. Exceptional adhesion. High solids. Fast Dry. Easy sand. Zero HAP.								

* Catalyzed VOC content