

CrystalVar™ 275 Sealer

WATER-CLEAR CONVERSION VARNISH SANDING SEALER

Product Code: **310607**

CrystalVar™ 275 Sanding Sealer is a water-clear, two-part acid catalyzed conversion varnish sanding sealer for use with CrystalVar 275 conversion varnish topcoats.

Ideal For

- Kitchen cabinets
- Bathroom cabinets
- Wood placed in high moisture areas
- Residential table and bar tops

- AIM compliant 275 g/l VOC
- NESHAP compliant—JJ (furniture)
- NESHAP compliant—QQQQ (doors & windows)

Performance Benefits

- Water Clear
- Non-yellowing
- Excellent water and chemical resistance
- 10 hour pot life
- Excellent flow and leveling
- High solids produces high build
- Excellent sanding properties
- Super-low HAP

APPLICATION DATA

SURFACE PREPARATION: “White sand” wood with maximum 150 grit aluminum oxide sandpaper. Remove all sanding dust. Keep free of dirt, grease, silicone oils, lubricants and other contaminants.

APPLICATION EQUIPMENT: This product is designed for spray application through all types of equipment. Mixing or pumping equipment that is in constant contact with Conversion Varnish should be constructed of stainless steel or other anti-corrosive material. The recommended settings below are with the trigger pulled.

Airless	No thinning required. Spray at 1000 or 1200 psi 411 or 513 tip
Air Assist	No thinning required. Spray at 700 to 900 psi fluid pressure 10-12 psi air cap 411 or 513 tip
HVLP	No thinning required. Spray at 28 psi through a 1.4 fluid nozzle

THINNING: This product is designed to spray at package viscosity with most application equipment. Thinning requirements may vary with changes in temperature and spray room conditions. If thinning is desired, use 652081 VOC Exempt Lacquer Thinner, 652210 No-HAP Lacquer Thinner, or Acetone.

Note: Thinning will reduce film build and may increase VOCs or HAPs, unless using VOC exempt or HAP-free solvents.

AGITATION: This product must be kept under slow, constant agitation, to ensure proper mixing.

CLEAN UP: Use acetone or compliant lacquer clean-up solvent.

FINISHING SYSTEM

MIXING DIRECTIONS: Add 6 fluid ounces of Rudd 03-143 Catalyst per gallon. Stir well during and after adding catalyst.

POT LIFE: 10 hours @ 65-70°F.

STAIN: When staining wood, use Rudd Colortools™ Low VOC Dye Stains, Colortools™ Low VOC Spray Only Stain, or Colortools™ 240 VOC Wiping Stain.

SEAL: Apply one coat (3-5 mils wet) of CrystalVar 275 Sealer. Allow to dry 35 minutes*. Sand with 220/320 grit silicon carbide sandpaper before finishing.

FINISH: Apply one or two coats (3-5 mils wet) of 310610 CrystalVar 275. Sand between all coats with 220/320 grit silicon carbide sandpaper.

If desired, additional coats may be applied up to a total dry film of 5.0 dry mils.

*Dry time will vary with film thickness, temperature, humidity & air flow.

SAFETY PRECAUTIONS

Avoid breathing vapors, use a NIOSH approved cartridge respirator. Use pre-filters to avoid breathing spray particles or sanding dust.

Flammable Liquid and Vapor: Keep away from heat, sparks and flame. Ensure adequate ventilation during use. Clean up spills with non-sparking tools and inert absorbent material. Store solvent and lacquer soaked rags and filters in water-filled, closed container prior to disposal. Dispose in safe, approved manner.

Read Safety Data Sheet and label before using.

SPECIFICATIONS

Coverage	600 square feet per gallon @ 1 mil dry film
Viscosity	16-19 Seconds (#2 Zahn @ 75°F)
Sag Resistance	4 mils vertical @ 65-70°F
Solids	42.1% by weight 3.6 lbs per gallon
VOC (Volatile Organic Compounds)	Calculated: 206 g/l (1.72 lb/gal) Catalyzed: 234 g/l (1.95 lb/gal)
HAP (Hazardous Air Pollutants)	Pounds HAP per Gallon: 0.0727 Pounds HAP per Pound Solids: < 0.8 (actual 0.0201) Pounds HAP per Volume Solids: < 0.48 (actual 0.1885)
Dry to Sand	35 minutes @ 65-70°F
CAUTION: Thinning will reduce film build and may increase VOCs or HAPs, unless using VOC exempt or HAP-free solvents.	

APPLICATION PRECAUTIONS

Do not use alkaline based products to clean surfaces finished with the CrystalVar 275 Clear Conversion Varnish system.

This product MUST be sanded between all coats to ensure proper adhesion. This product MUST be re-coated within 8 hours of being sanded.

This product is not recommend for exterior use.

Finish, substrate and curing temperatures should remain above 60°F, extremes of temperature and humidity may affect product performance.

Total film build of system must not exceed 5.0 dry mils.

This product has been tested on a limited number of substrates and over a limited number of coatings. The user is responsible for testing suitability and performance for their specific application.

Designed for professional use with spray application only.

Shipping & Storage Information

Flash Point: -4°F Pensky-Martin

OSHA Flammability Class: Flammable Liquid—Class IB

DOT Class: Paint, 3, UN 1263, PG II



RUDD COMPANY, INC

Manufacturers of Quality Coatings Since 1912

Gemini Industries, Inc., 421 SE 27th St, El Reno, OK 73036

ruddwoodfinishes.com · 800 262-5710

To the best of our knowledge the technical data contained herein are true and accurate at the date of issuance and are subject to change without prior notice. User must contact Rudd Company, Inc. to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Rudd Company, Inc. quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY THE SELLER, EXPRESSED OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.