

DuraCat™ 275

WATER-CLEAR PRE-CATALYZED LACQUER

Product Code: **651885NF**

DuraCat™ 275 is a water-clear pre-catalyzed lacquer ideal for residential and commercial interior wood surfaces.

Ideal for

Doors & Millwork
Cabinetry
Casegoods
Fixture & Display
Furniture
Interior Wood Work

Exceeds KCMA performance tests
AIM compliant 275 g/l VOC
NESHAP compliant—JJ (furniture)
NESHAP compliant—QQQQ (doors & windows)

Benefits

Water-Clear
Non-yellowing
Excellent abrasion & water resistance
Low odor
Excellent flow and leveling
Superior bubble release & film clarity
Enhanced blush resistance
Excellent sanding properties
Use with companion sanding sealer or self-seal
Ultra low HAP

APPLICATION DATA

SURFACE PREPARATION: “White sand” wood with maximum 150 grit aluminum oxide sandpaper. Remove all sanding dust. Keep free of dirt, grease, silicone oils, lubricants and other contaminants.

APPLICATION EQUIPMENT: This product is designed for spray application through all types of equipment. The recommended settings below are with trigger pulled.

Airless	No thinning required. Spray at 1000 to 1200 psi 411 or 513 tip
Air Assist	No thinning required. Spray at 700 to 900 psi fluid pressure 10-12 psi air cap 411 or 513 tip
HVLP	No thinning required. Spray at 28 psi through a 1.4 fluid nozzle

THINNING: This product is designed to spray at package viscosity with most application equipment. Thinning requirements may vary with changes in temperature and spray room conditions. If thinning is desired, use 652081 VOC Exempt Lacquer Thinner, 652210 No-HAP Lacquer Thinner, or Acetone.

Note: Thinning will reduce film build and may increase VOCs or HAPs, unless using VOC exempt or HAP-free solvents.

AGITATION: This product must be kept under slow, constant agitation, to ensure proper mixing.

CLEAN UP: Use acetone or suitable VOC compliant clean-up solvent.

FINISHING SYSTEM

STAIN: When staining wood, use Rudd Colortools™ Low VOC Dye Stain, Colortools™ Low VOC Spray Only Stain, or Colortools™ Low VOC Wiping Stain.

SEAL: Apply one coat (3-5 mils wet) of 651825 DuraCat 275 PreCat Sealer or use DuraCat 275 PreCat Finish as its own sealer. Allow to dry 20 minutes*, sand with 220/320 grit silicon carbide sandpaper before finishing.

FINISH: Apply two coats (3-5 mils wet) of DuraCat 275 PreCat Finish. Allow 20 minutes* dry time and sand with 220/320 grit silicon carbide sandpaper between coats.

If desired, additional coats may be applied up to a total dry film of 5.0 dry mils.

*Dry times may vary with film thickness, temperature, humidity and air

SAFETY PRECAUTIONS

Avoid breathing vapors, use a NIOSH approved cartridge respirator. Use pre-filters to avoid breathing spray particles or sanding dust.

Flammable Liquid and Vapor: Keep away from heat, sparks and flame. Ensure adequate ventilation during use. Clean up spills with non-sparking tools and inert absorbent material. Store solvent and lacquer soaked rags and filters in water-filled, closed container prior to disposal. Dispose in safe, approved manner.

Read Safety Data Sheet and label before using.

FINISH PERFORMANCE TESTING

KCMA	
Vinegar	No Visual Effect
Lemon Juice	No Visual Effect
Orange Juice	No Visual Effect
Grape Juice	No Visual Effect
Catsup	No Visual Effect
Olive Oil	No Visual Effect
100 Proof Alcohol	No Visual Effect
Hot Coffee	No Visual Effect
Edge Soak	Passed 24 hr KCMA test with no softening, discoloration or film defects
Cold Check	Passed 20 cycles @ 5 mils dry film
OTHER	
Pencil Hardness	Pass 2B
Mar Resistance	Excellent
Adhesion	Excellent

*** Contact your Sales Representative for available stock sheens and package sizes.***

SPECIFICATIONS

Coverage	275 square feet per gallon @ 1 mil dry film thickness
Viscosity	17-19 seconds (#2 Zahn Cup @ 77°F)
Sag Resistance	5 mils vertical @ 65-70°F
Solids*	23.7-25.0% by weight 1.8-1.9 lbs per gallon
VOC* (Volatile Organic Compounds)	Calculated: 266-274 g/l (2.22-2.28 lb/gal)
HAP* (Hazardous Air Pollutants)	Pounds HAP per Gallon: 0.0682—0.0683 Pounds HAP per Pound Solids: < 0.8 (actual 0.0357—0.0379) Pounds HAP per Volume Solids: <0.48 (actual 0.3744—0.3930)
Dry to Sand	20 minutes @ 65-70°F
Block Free	16 hours @ 5 mils wet
*Variations depend on gloss. CAUTION: Thinning will reduce film build and may increase VOCs or HAPs, unless using VOC exempt or HAP-free solvents.	

APPLICATION PRECAUTIONS

DuraCat 275 PreCat has a limited shelf life of approximately 6 months from date of manufacture. Usability and performance may not always be determined by viscosity. Shelf life will vary with storage conditions.

Do not use DuraCat 275 PreCat as a topcoat over stearated sanding sealers. Use DuraCat 275 PreCat Sealer or use DuraCat 275 PreCat Finish as its own sealer.

Do not use DuraCat 275 in heated spray equipment.

Finish, substrate and curing temperatures should remain above 60° F, extremes of temperature and humidity may affect product performance.

Total film build of finishing system must not exceed 5.0 dry mils.

This product is not recommended for exterior use.

Clear finishes will not prevent natural (unstained) wood from changing color over time.

This product has been tested on a limited number of substrates and over a limited number of coatings. The user is responsible for testing suitability and performance for their specific application.

Designed for professional use by spray application only.

Shipping & Storage Information

Flash Point: -4° F Pensky-Martin

OSHA Flammability Class: Flammable Liquid—Class IB

DOT Class: Paint, 3, UN 1263, PG II



Gemini Industries, Inc. • 421 SE 27th St. • El Reno, OK 73036
ruddwoodfinishes.com • 800 262-5710

To the best of our knowledge the technical data contained herein are true and accurate at the date of issuance and are subject to change without prior notice. User must contact Rudd Company, Inc. to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Rudd Company, Inc. quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY THE SELLER, EXPRESSED OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.